

AD-A141 558

ORGANOSILANE POLYMERS VI BRANCHED POLYSILAHYDROCARBON
PRECURSORS FOR SILICON CARBIDE(U) UNION CARBIDE CORP
TARRYTOWN NY C L SCHILLING ET AL. SEP 83 TR-83-2
N00014-81-C-0682


1//

UNCLASSIFIED

F/O 7/3

NL





MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS - 1963-A

AD-A141 558

DTIC FILE COPY

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER 83-2	2. GOVT ACCESSION NO. AD A141558	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) Organosilane Polymers, VI Branched Polysilanehydrocarbon Precursors for Silicon Carbide		5. TYPE OF REPORT & PERIOD COVERED Technical
7. AUTHOR(s) C. L. Schilling, Jr. and T. C. Williams		6. PERFORMING ORG. REPORT NUMBER
9. PERFORMING ORGANIZATION NAME AND ADDRESS Union Carbide Corporation Tarrytown, N. Y., 10591		8. CONTRACT OR GRANT NUMBER(s) N-00014-81-C-0682
11. CONTROLLING OFFICE NAME AND ADDRESS Chemistry Branch Office of Naval Research Arlington, Virginia 22217		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		12. REPORT DATE September 1983
		13. NUMBER OF PAGES
		13. SECURITY CLASS. (of this report) Unclassified
		13a. DECLASSIFICATION/DOWNGRADING SCHEDULE
15. DISTRIBUTION STATEMENT (of this Report) Technical Report Distribution List This document has been approved for public release and sale; its distribution is unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES To be presented in part at the 1984 Spring Meeting of the American Chemical Society.		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Polysilanehydrocarbons Copolymer Polycarbosilanes Organopolysilanes Silanes Ceramics		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Polysilanehydrocarbon precursors for silicon carbide ceramic compositions have been prepared by potassium dechlorination reactions of mixtures of chlorosilanes and hydrocarbon olefins such as styrene or isoprene. The presence of branched silyl units in the polymer backbones is critical in providing significant ceramic yields.		

DD FORM 1 JAN 73 1473

EDITION OF 1 NOV 65 IS OBSOLETE
S/N 0102-014-6631

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

84 05 29 040

MAY 30 1984

OFFICE OF NAVAL RESEARCH
CONTRACT N00014-81-C-0682
TECHNICAL REPORT 83-2

ORGANOSILANE POLYMERS, VI:

BRANCHED POLYSILAHYDROCARBON

PRECURSORS FOR SILICON CARBIDE

by

C. L. Schilling Jr. and T. C. Williams

Union Carbide Corporation
Tarrytown, New York 10591

Reproduction in whole or in part is permitted
for any purpose of the United States Government

This document has been approved for public
release and sale; its distribution is unlimited

September 1983

84 05 29 040


ORGANOSILANE POLYMERS, VI:
BRANCHED POLYSILAHYDROCARBON PRECURSORS
FOR SILICON CARBIDE

INTRODUCTION

In the course of developing highly branched polycarbosilane precursors for silicon carbide ceramic compositions,¹ it was recognized that tri- or tetra-functional branching silyl units were critical in obtaining effective SiC yields. It was also felt that the same structural approach, i.e., branched silyl units, would provide improved ceramic yields if applied to polysilahydrocarbons (copolymers consisting of silyl monomer units and units derived from hydrocarbon olefins, such as styrene or isoprene). The concept has been validated, with further improvements in ceramic yield being obtained by incorporation of hydrosilyl (SiH) monomer units.


RESULTS AND DISCUSSION

Linear polysilahydrocarbons known in the open literature were prepared and compared with corresponding polymers which contained branching silyl units. For example, a linear copolymer derived from Me_2SiCl_2 and styrene^{2,3} was prepared using potassium metal in tetrahydrofuran solvent (K/THF) as the dechlorinating medium. Pyrolysis of the linear polymer to 700° under an inert




atmosphere provided 3.4% of SiC ceramic composition. An analogous branched copolymer, prepared with a lower molar ratio of MeSiCl_3 , provided 28.0% of SiC ceramic composition when pyrolyzed to 1200° .

Similarly, a copolymer from Me_2SiCl_2 and isoprene⁴ yielded 0.8% of ceramic composition, while the corresponding branched copolymer prepared with MeSiCl_3 provided 25.0% of SiC-containing ceramic.




The lower molar ratio of MeSiCl_3 to olefin (0.67 relative to 1.0 for Me_2SiCl_2) was used to balance Si-reactive sites (SiCl groups) and C-reactive sites (two per molecule for styrene or isoprene), maximizing formation of Si-C bonds.

Isoprene was also incorporated into a typical polycarbosilane (product from 0.85/0.3/1.0 molar mixture of $\text{Me}_3\text{SiCl}/\text{Me}_2\text{SiCl}_2/\text{CH}_2=\text{CHSiMeCl}_2$ and K/THF) as a substitute for Me_2SiCl_2 . While the ceramic yield was lower (31.4% for the



Me_2SiCl_2 version), the product demonstrates the effectiveness of $\text{CH}_2=\text{CHSiMeCl}_2$ in providing backbone branching in polysilahydrocarbons.


An effective SiC precursor was also obtained using $\text{ClCH}_2\text{SiMeCl}_2$ as the branching silyl monomer. The 2/1 molar ratio of $\text{ClCH}_2\text{SiMeCl}_2/\text{CH}_2=\text{CHCMe}=\text{CH}_2$ was




also used to balance C-reactive sites ($\text{CH}_2=$ and ClCH_2- groups) with Si-reactive sites, (SiCl groups), and provided a corresponding increase in ceramic yield.

A similar precursor prepared from 2/1 $\text{ClCH}_2\text{SiMeCl}_2$ /styrene also provided a high ceramic yield (60.4%), but was an intractable, insoluble solid.

MeSiHCl_2 provides both backbone branching units and difunctional hydrosilyl units in polycarbosilanes,⁵ and is similarly incorporated into polysilahydrocarbon structures.⁶ The product from $\text{MeSiHCl}_2/\text{CH}_2=\text{CHCMe}=\text{CH}_2$, although






$$(x + y = 1, x \cong 0.8)$$

obtained in low yield (21.1% as nonvolatile polymer) was an excellent SiC precursor, providing bulk pieces with higher integrity and density than obtained from the other polysilahydrocarbons. This product, a low viscosity fluid, should perform well as a preceramic adhesive, binder, or coating.

The reaction between MeSiHCl_2 and isoprene using magnesium metal in THF (Mg/THF) is reported to yield 1,3-dimethyl-1-silacyclopent-3-ene, plus a polymer.⁷ While similar results were obtained by us, the Mg-derived polymer is not an effective SiC precursor (10.6% yield in pyrolysis to 700°) when compared to the K-derived polymer. Spectral and elemental analyses of the K-derived polymer show it to be higher in contained silicon than expected, probably due to formation of SiSi bonds and resultant lower incorporation of isoprenoid units.

Conversely, the major volatile products of the K reaction, before aqueous termination and neutralization, are isomers of 2-methyl-1,4-di[1-(1,3-dimethyl-1-silacyclopent-3-enyl)-2-butene (I), as identified by mass spectrometry and NMR analyses. Compound I is cleaved to a significant extent by



the acidic aqueous workup to 1-(3-methylbut-3-enyl)-1,3-dimethyl-1-silacyclopent-3-ene, II, and a disiloxane, III (see Figures 1, 2 and 3 for respective GC/MS patterns for Compounds I, II and III). Acidic aqueous cleavage of 1,4-disilyl isoprenoid groups has been reported,⁸ and no doubt occurs as well with linear polymeric products in the present work.

Polymer Properties

The polysilahydrocarbons reported herein range from low viscosity fluids, such as the nonvolatile K-derived product from $\text{MeSiHCl}_2/\text{CH}_2=\text{CHCMe}=\text{CH}_2$, to insoluble solids, such as that derived from $2/1 \text{ ClCH}_2\text{SiMeCl}_2/\text{CH}_2=\text{CHCMe}=\text{CH}_2$. With the latter exception, only soluble, nonvolatile products were screened in pyrolyses.

These polymers are not amenable to exact elemental analyses due to oxygen incorporation during hydrolytic termination/neutralization, loss of hydrogen from hydrosilyl groups during reactions, differing contents of silyl and hydrocarbon units in volatile and nonvolatile fractions, and problems in completely combusting preceramic polymers.⁹ They are amenable to typical thermal analyses, and to the study of molecular weight distributions by gel permeation chromatography.

EXPERIMENTAL

All chlorosilanes were freshly distilled before use. THF was reagent grade, dried over Linde 4A molecular sieves. K Metal was purchased as practical grade ingots; all K metal transfers were made under nitrogen in a dry box. All reactions (preparations and pyrolyses) were run under argon or nitrogen. Routine NMR spectra were recorded on a Perkin-Elmer R24A spectrometer - VPC Analyses were run on a Hewlett-Packard 5840A gas chromatograph. Pyrolyses up to 700° were run in quartz reactors in a Lindberg 54242 tube furnace and those up to 1200° were run in an alumina reactor in a Lindberg 54233 tube furnace. Both furnaces have programmable controllers, which allow attendant-free operation from charging to removal of products. Conversion to SiC compositions were confirmed by x-ray diffraction. Pyrolysis programs are given in Reference 1b.

Reaction of 1/1 Me₂SiCl₂/CH₂=CH₂ with K in THF

K metal (21.3g, 0.54 mol) and 179.3g of THF were combined in a 500 ml 3-necked round-bottomed flask, which was then fitted with mechanical stirrer (stainless steel blade), thermometer, addition funnel, Dewar condenser (filled with toluene cooled with ice water immersion coil), and valves for maintaining a nitrogen atmosphere. The addition funnel was charged with 33.5g (0.26 mol) of Me₂SiCl₂ and 27.0g (0.26 mol) of freshly distilled styrene, and contents of the flask heated to reflux, melting the K. Addition of the monomer mixture was completed in 31 min., and the reaction mixture then heated at reflux for 3 hours, followed by cooling, termination by the cautious dropwise addition of 6.63g H₂O in 17.24g THF, and neutralization with 2.5g conc. HCl. Solids were removed by filtration, and the THF solution dried over MgSO₄. Refiltration and vacuum stripping provided 41.2g (97.8%) of soluble solid product. Pyrolysis of this material to 700° left only 3.4% of ceramic.

Reaction of 1/1 Me₂SiCl₂/CH₂=CHCMe=CH₂ with K in THF

The above procedure was repeated using 23.5g (0.6 mol) of K metal, 421.7g of THF, and a mixture of 36.8g (0.29 mol) of Me₂SiCl₂ and 19.4g (0.29 mol) of isoprene. Reaction mixture was heated at reflux for five hours after completion of addition and was worked up as above. Workup yielded 10.6g (29.6%) of nonvolatile polymer, b.p. greater than 88°/0.5 mm, plus volatile products. Pyrolysis of the polymer to 700° left only 0.8% of ceramic residue.

Reaction of 2/3 MeSiCl₃/CH₂=CH₂ with K in THF

The experimental procedure was followed with 22.8g (0.58 mol) of K metal, 172.9g of THF, and a mixture of 27.5g (0.18 mol) of MeSiCl₃ and 28.8g (0.28 mol) of styrene. Reaction was heated for four hours after end of addition. Workup as above provided a 50.0% yield of soluble solid and 34.4% of insoluble solid (latter isolated by aqueous extraction of KCl filter cake, followed by water washing and vacuum drying of solid organic product). Pyrolysis of the soluble solid to 1200° in two steps yielded 28.0% of SiC ceramic composition. Its x-ray diffraction pattern was correct for microcrystalline β -SiC.¹⁰

Reaction of 2/3 MeSiCl₃/CH₂=CHCMe=CH₂ with K in THF

The above procedure was followed with 27.6g (0.71 mol) of K metal, 408.8g of THF, and a mixture of 33.5g (0.22 mol) of MeSiCl₃ and 22.8g (0.34 mol) of isoprene. Workup yielded 28.2g (85.2%) of soluble solid, b.p. greater than 28°/0.08 mm. Pyrolysis to 1200° provided 25.0% of SiC composition, having the correct x-diffraction pattern for microcrystalline β -SiC.

Reaction of 0.85/0.3/1.0 Me₃SiCl/CH₂=CHCMe=CH₂/CH₂=CHSiMeCl₂ with K in THF

The experimental procedure was repeated with 23.6g (0.60 mol) of K metal, 289.4g of THF, and a mixture of 18.6g (0.17 mol) of Me₃SiCl, 4.1g (0.06 mol) of isoprene, and 28.5g (0.2 mol) of CH₂=CHSiMeCl₂. Workup yielded 18.8g (61.1%) of soluble solid, which pyrolyzed to 23.3% of SiC ceramic composition (1200°, two steps).

Reaction of 1/1 MeSiHCl₂/isoprene with K/THF

In a 11 3N RB flask were combined 373.5g of THF and 31.42g (0.804 mol) of K metal. Flask was fitted with mechanical stirrer (stainless steel blade), thermometer, addition funnel, condenser, and N₂ flow valves with bubbler. Heat was applied to reflux, melting the K, and addition of a solution of 43.7g (0.38 mol) of MeSiHCl₂ and 25.5g (0.38 mol) of isoprene begun. Addition continued intermittently (due to viscosity buildup) with continuous heating until completed (205 min). Reaction took on a rust color shortly after each incremental addition, with the color fading to clear during each addition. Additional THF (280 ml) was added to reduce viscosity and heating continued at reflux for 2 hr. Reaction was cooled on wet ice bath, terminated with a solution of 12.2g H₂O in 49.9g THF, and neutralized with 8g conc. HCl (weakly acidic by pH paper test). KCl was removed by filtration, triturated with THF, and the combined THF solution dried over MgSO₄. Dissolution of the KCl in water disclosed no insoluble organic products. The THF solution was filtered to remove MgSO₄, followed by stripping and vacuum distillation, yielding 8.93g (21.1%) of heavies, b.p. above 158°/0.24 mm, and 26.57g (63.0%) of volatile products, b.p. up to 158°/0.24 mm. Pyrolysis of the heavies to 1200° in two steps provided 49.5% of hard, black, dense, glossy ceramic chips. The x-ray diffraction pattern was correct for microcrystalline β -SiC.

A similar sample from a repeat preparation analyzed as follows: Cal'd: % C, 61.59, % H, 10.60, % Si, 27.81, % O (by difference) 0.00; Found: % C, 46.71, % H, 9.42, % Si, 37.95, % O (by difference) 5.80, % Cl, 0.12. Analysis confirms that silyl units are more concentrated in the heavies than in the volatile products, contributing to the high SiC yield.

Reaction of 1/1 MeSiHCl₂/CH₂=CH \emptyset with K in THF

The above procedure was repeated using 60.22g (1.54 mol) of K metal, 802.1g of THF, and a mixture of 84.46g (0.734 mol) of MeSiHCl₂ and 76.5g (0.734 mol) of styrene. Workup yielded 96.95g (89%) of nonvolatile polymer, which pyrolyzed (1200°, 2 steps) to 25.1% of SiC ceramic composition.


Reaction of 2/1 ClCH₂SiMeCl₂/CH₂=CHCMe=CH₂ with K in THF

The procedure was followed with 22.3g (0.57 mol) of K metal, 413.0g of THF, and a mixture of 29.53g (0.18 mol) of ClCH₂SiMeCl₂ and 6.14g (0.09 mol) of isoprene. An additional 120 ml of THF was added during the reaction to reduce viscosity. Workup yielded 37.7% of volatile products, 40.6% of nonvolatile polymer, and 4.5% of insoluble solid product. Pyrolysis of the nonvolatile polymer to 1200° provided 45.5% of SiC composition.


REFERENCES

- 1a. C. L. Schilling, J. P. Wesson, and T. C. Williams, Am. Ceram. Soc. Bull., 62, 912 (1983).
- b. J. Poly. Sci., Polymer Symposia, in press.
- c. ONR Technical Report TR-80-1, see Chem. Abstr., 95, 170175q (1981).
- 2a. D. R. Weyenberg et. al., J. Org. Chem., 30, 4096 (1965).
- b. U. S. Patent 3,187,031, June 1, 1965.
3. O. M. Nefedov et. al., Proc. Acad. Sci. USSR, 1962, p 1152, (English Translation).
- 4a. D. R. Weyenberg et. al., J. Org. Chem., 33, 1975 (1968).
- b. U. S. Patent, 3,187,032, June 1, 1965.
5. C. L. Schilling and T. C. Williams, Organosilane Polymers, V. Hydrosilyl-Modified Polycarbosilane Precursors for Silicon Carbide, ONR Technical Report 83-1, in press.
6. O. M. Nefedov et. al., Chem. Heterocyclic Comp., 2, 215 (1966), (English Translation).
7. G. Manuel et. al., Syn. React. Inorg. Metal-Org. Chem., 4, 133 (1974).
8. J. Dunogues et. al., J. Organometal Chem., 63, 19 (1973).
9. Elemental analyses by Galbraith Laboratories, Knoxville, Tennessee.
10. S. Yajima et. al., Nature, 279, 706 (1979).

FIGURE 1




Spectrum # 217.038 ** Sample # 1256 Retention Time = 14.4 min
 Scanned from 10 to 600 amu Number of peaks Detected = 115
 File type = linear
 Base Peak = 111.00 Base Peak Abundance = 459 Total Abundance = 1479




Lower Abundance Cutoff Level = 5.0%

MASS	ABUNDANCE (%)	MASS	ABUNDANCE (%)	MASS	ABUNDANCE (%)
17.05	0.5	95.05	5.5	117.05	5.5
29.05	0.5	97.05	5.5	119.05	5.5
43.05	12.2	99.05	5.5	121.05	5.5
55.05	0.5	109.00	10.5	123.00	5.5
59.05	11.5	110.00	5.5	125.00	5.5
71.05	5.0	111.00	45.9	127.00	11.5
83.05	10.9	112.00	11.5	129.00	18.7
94.95	7.2	113.00	6.1	131.00	12.9
94.95	13.3	123.00	5.5	133.00	5.2

FIGURE 2




Spectrum # 191.038 ** Sample # 1256 Retention Time = 1 minutes
 Scanned from 10 to 600 amu Number of Peaks Detected = 77
 File type = linear
 Base Peak = 111.00 Base Peak Abundance = 3115 Total Abund = 18915



Lower Abundance Cutoff Level = 5.0%


MASS	ABUNDANCE (%)	MASS	ABUNDANCE (%)	MASS	ABUNDANCE
41.00	7.7	83.00	10.9	110.00	50.7
43.05	30.7	95.05	8.0	111.00	100.0
45.05	8.6	97.05	11.2	112.00	13.7
54.95	5.2	109.00	20.9	120.05	13.2
59.95	5.6				

FIGURE 3



Spectrum # 199.038 ** Sample # 1256 Retention Time = 9.3 minutes
 Scanned from 10 to 300 and Number of Peaks Detected = 132
 File type = linear

Base Peak = 155.00 Base Peak Abundance = 353 Total Abundance = 5155



Lower Abundance Cutoff Level = 5.0%

MASS	ABUNDANCE (%)	MASS	ABUNDANCE (%)	MASS	ABUNDANCE
97.00	3.7	97.00	12.6	157.00	13.1
98.00	0.1	102.95	20.7	160.00	0.4
99.00	0.0	103.95	20.6	169.00	22.1
101.00	31.0	105.00	0.1	170.00	40.0
104.00	10.4	109.00	20.9	171.00	17.0
105.00	35.4	110.00	13.1	171.95	7.5
106.00	0.4	111.00	66.0	180.95	40.0
107.00	0.0	111.00	10.0	181.95	10.0
108.00	0.0	113.00	6.1	183.00	1.0
109.00	0.0	115.00	0.1	195.00	0.4
110.00	0.0	116.00	12.0	196.00	0.0
111.00	0.0	118.00	7.0	197.00	0.0
112.00	0.0	126.95	7.0	199.00	0.0
113.00	0.0	127.95	19.0	209.00	0.0
114.00	0.0	129.00	27.7	210.95	1.0
115.00	0.0	129.95	9.9	220.00	79.4
116.00	0.0	130.95	9.2	224.00	17.0
117.00	0.0	140.95	10.0	225.00	0.0
118.00	0.0	141.95	75.4	238.10	0.0
119.00	0.0	142.95	20.2	239.10	20.7
120.00	0.0	143.95	0.4	240.10	0.4
121.00	0.0	155.00	100.0		
122.00	0.0	156.00	10.7		

DL/413/83/01
GEN/413-2

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Attn: Code 413 800 N. Quincy Street Arlington, Virginia 22217	2	Naval Ocean Systems Center Attn: Technical Library San Diego, California 92152	1
ONR Pasadena Detachment Attn: Dr. R. J. Marcus 1030 East Green Street Pasadena, California 91106	1	Naval Weapons Center Attn: Dr. A. B. Amster Chemistry Division China Lake, California 93555	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Washington, D.C. 20360	1	Scientific Advisor Commandant of the Marine Corps Code RD-1 Washington, D.C. 20380	1
Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1	Dean William Tolles Naval Postgraduate School Monterey, California 93940	1
Superintendent Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1	U.S. Army Research Office Attn: CRD-AA-IP P.O. Box 12211 Research Triangle Park, NC 27709	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Mr. Vincent Schaper DTNSRDC Code 2830 Annapolis, Maryland 21402	1
DTNSRDC Attn: Dr. G. Bosmajian Applied Chemistry Division Annapolis, Maryland 21401	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1
Naval Ocean Systems Center Attn: Dr. S. Yamamoto Marine Sciences Division San Diego, California 91232	1	Mr. A. M. Anzalone Administrative Librarian PLASTEC/ARRADCOM Bldg 3401 Dover, New Jersey 07801	1

DL/413/83/01
3568/413-2

TECHNICAL REPORT DISTRIBUTION LIST, 3568

Dr. C. L. Schilling
Union Carbide Corporation
Chemical and Plastics
Tarrytown Technical Center
Tarrytown, New York

Dr. A. G. MacDiarmid
Department of Chemistry
University of Pennsylvania
Philadelphia, Pennsylvania 19174

Dr. E. Fischer, Code 2853
Naval Ship Research and
Development Center
Annapolis, Maryland 21402

Dr. H. Allcock
Department of Chemistry
Pennsylvania State University
University Park, Pennsylvania 16802

Dr. M. Kenney
Department of Chemistry
Case Western University
Cleveland, Ohio 44106

Dr. R. Lenz
Department of Chemistry
University of Massachusetts
Amherst, Massachusetts 01002

Dr. M. David Curtis
Department of Chemistry
University of Michigan
Ann Arbor, Michigan 48105

NASA-Lewis Research Center
Attn: Dr. T. T. Serafini, MS 49-1
21000 Brookpark Road
Cleveland, Ohio 44135

Dr. J. Griffith
Naval Research Laboratory
Chemistry Section, Code 6120
Washington, D.C. 20375

Professor G. Wnek
Department of Materials Science
and Engineering
Massachusetts Institute of Technology
Cambridge, Massachusetts 02139

Dr. R. Soulen
Contract Research Department
Pennwalt Corporation
900 First Avenue
King of Prussia, Pennsylvania 19406

Dr. G. Goodman
Globe-Union Incorporated
5757 North Green Bay Avenue
Milwaukee, Wisconsin 53201

Dr. Martin H. Kaufman
Code 38506
Naval Weapons Center
China Lake, California 93555

Dr. C. Allen
Department of Chemistry
University of Vermont
Burlington, Vermont 05401

Professor R. Drago
Department of Chemistry
University of Florida
Gainesville, Florida 32611

Dr. D. L. Venezky
Code 6130
Naval Research Laboratory
Washington, D.C. 20375

Professor T. Katz
Department of Chemistry
Columbia University
New York, New York 10027

Professor James Chien
Department of Chemistry
University of Massachusetts
Amherst, Massachusetts 01002

Professor J. Salamone
Department of Chemistry
University of Lowell
Lowell, Massachusetts 01854

Dr. S. Cooper
Department of Chemistry
University of Wisconsin
750 University Avenue
Madison, Wisconsin 53706

DL/413/83/01
356B/413-2

TECHNICAL REPORT DISTRIBUTION LIST, 356B

Professor D. Grubb
Department of Materials Science
and Engineering
Cornell University
Ithaca, New York 14853

Professor T. Marks
Department of Chemistry
Northwestern University
Evanston, Illinois 60201

Professor C. Chung
Department of Materials Engineering
Rensselaer Polytechnic Institute
Troy, New York 12181

Professor Malcolm B. Polk
Department of Chemistry
Atlanta University
Atlanta, Georgia 30314

Dr. D. B. Cotts
SRI International
333 Ravenswood Avenue
Menlo Park, California 94205

Dr. Kurt Baum
Fluorochem, Inc.
680 S. Ayon Avenue
Azusa, California 91702

Professor H. Hall
Department of Chemistry
University of Arizona
Tucson, Arizona 85721

Professor G. Whitesides
Department of Chemistry
Harvard University
Cambridge, Massachusetts 02138

Professor H. Ishida
Department of Macromolecular Science
Case Western University
Cleveland, Ohio 44106

Dr. K. Paciorek
Ultrasystems, Inc.
P.O. Box 19605
Irvine, California 92715

Professor D. Seyferth
Department of Chemistry
Massachusetts Institute of Technology
Cambridge, Massachusetts 02139

Dr. G. Bryan Street
IBM Research Laboratory, K32/281
San Jose, California 95193

CAPT J. J. Auburn, USNR
AT&T Bell Laboratories
Room 6F-211
600 Mountain Avenue
Murray Hill, New Jersey 07974

JUN 09, 1984

PAGE 2

UNCLASSIFIED

TR

FIELD/GROUP eeeee

00 00 A141558 (U)

UNCLASSIFIED TITLE

ORGANOSILANE POLYMERS. VI. BRANCHED POLYSILANHYDROCARBON PRECURSORS FOR SILICON CARBIDE.

ABSTRACT

(U) POLYSILANHYDROCARBON PRECURSORS FOR SILICON CARBIDE CERAMIC COMPOSITIONS HAVE BEEN PREPARED BY POTASSIUM DECHLORINA
TION REACTIONS OF MIXTURES OF CHLOROSILANES AND HYDROCARBON OLEFINS SUCH AS STYRENE OR ISOPRENE. THE PRESENCE OF BRANC
HED SILYL UNITS IN THE POLYMER BACKBONES IS CRITICAL IN PROVIDING SIGNIFICANT CERAMIC YIELDS. (AUTHOR)

POSTING TERMS ASSIGNED

CERAMIC YIELDS
USE CERAMIC MATERIALS
YIELD

CHLOROSILANES
USE CHLOROSILANES

HYDROCARBON OLEFINS
USE HYDROCARBONS
OLEFIN-POLYMERS

ISOPRENE
USE ISOPRENE

ORGANOSILANE POLYMERS
USE ORGANIC COMPOUNDS
POLYMERS
SILANES

SILICON CARBIDE
USE SILICON CARBIDES

SILICON CARBIDE CERAMIC COMPOSITIONS
USE CERAMIC MATERIALS
CONCENTRATION(COMPOSITION)
SILICON CARBIDES

PHRASES NOT FOUND DURING LEXICAL DICTIONARY MATCH PROCESS

UNCLASSIFIED

END

DATE
FILMED

7-84

DTIC